



# LEADERS IN WAX TECHNOLOGY

THE FINEST NATURAL WAXES IN THE WORLD SINCE 1904

## OZOKERITE WAX SPECIFICATIONS

White Ozokerite Wax			
S&P Number	Melting Point	Penetration 100/25 Deg.C/5	Gel Strength
SP-271P	84.4°C -95.6°C	8-14	65-100
SP-273P	87.8°C – 96.1°C	4-10	65-85
SP-996	73.9°C – 78.3°C	6-12	80-110
SP-1016	71.1°C – 74.4°C	9-15	120 Max
SP-1020	73.3°C -76.1°C	8-13	150 Max
SP-1021	74.4°C – 77.2°C	8-13	160 Max
SP-1025	68.3°C – 71.1°C	10-15	112-120
SP-1026	76.1°C – 78.9°C	8-14	65-95
SP-1028	72.8°C – 76.1°C	7-13	100-130
SP-1190	79.4°C -85°C	8-14	65-95
SP-2020 *	73.9°C – 79.4°C	10-20	
SP-2021 *	75.0°C -80.6°C	6-15	
SP-2026 *	79.4°C -85.0°C	6-12	
SP-2173 *	62.7°C – 68.3°C	10-16	
SP-2101 *	76.1°C – 81.7°C	6-15	
SP-2190 *	79.4°C -85.0°C	6-14	
SP-2248 *	64.4°C – 67.8°C	7-13	
SP-2673 *	60.0°C -65.6 °C	8-16	
* COLPIA COMPLIANT			